# An Overview; Wastewater Treatment Using Biochar to Reduce Heavy Metals

Yudha Gusti Wibowo<sup>1</sup>, Desy Rosarina<sup>2</sup>, Frena Fardillah<sup>2</sup>, Dhani Windra Gusva<sup>1</sup> and Anis Tatik Maryani<sup>1</sup>

<sup>1</sup>Postgraduate Program, Universitas Jambi <sup>2</sup>Department of Industrial Engineering, Universitas Muhammadiyah Tangerang

<sup>\*)</sup>Penulis untuk korespondensi: Tel./Faks. +62813 7364 5090

email: yudhagustiwibowo26@gmail.com

### ABSTRACT

Environmental management is a issue in recent decades such as waste production by indutry especially wastewater. Needed biomaterial to solve wastewater problem caused biomaterial is a green material give not negative impact for environment. Biochar is a green leap toward reducing heavy metals content on wastewater using coconut shell waste. Biochar has been world used in many studies and practical applications are only limited to remediation of contaminants on soil. This paper describes the basic understanding and recent development biochar as an innovative solution for treating wastewater. Thus, this paper is expected to provide clear information about biochar to reducing heavy metals content on wastewater and inspiration for ongoing and future research benefit.

Keywords: Environmental managament, Wastewater, Biochar, Heavy metals.

### **INTRODUCTION**

Environmental management is a issue in recent decades (Ruokonen & Temmes, 2019) such as climate change (Lejano, 2019), solid waste (Pfennigstorf, 1979), soil (Boddu et al., 2018), wastewater (de Matos et al., 2017) and air pollution (Pfennigstorf, 1979) will give negative impact for human health (Sun et al., 2018) and environment (Mandal & Kaur, 2019). biochar has attracted much attention due to its promising role in many environmental management issues (Kumar, Loganathan, Gupta, & Barnett, 2011)Biochar is a product of pyrolysis, gasification and combustion process (Bridgwater, 2012) can be produced by all of organic materials (Zhikun Zhang, Zhu, Shen, & Liu, 2019).

This review aims to present the efficiency of biochar in wastewater treatment and biochar production by conventional conversion of coconut-shell biomass. Wastewater is a liquid waste that dangerous for environment and will give some impact for human health (Nzediegwu et al., 2019) and ecological balance (Gupta et al, 2009). The review also presents recent advances on coconut cultivation, and conversion of harvested biomass with the focus on biochar production through pyrolysis process.

#### WASTEWATER TREATMENT USING BIOCHAR

Biochar is a biomaterial has producing by organic matters, organic material that potential to creat biochar is coconut-shell (Xu et al., 2018). Indonesia is a big country that produce organic waste 64 billion tons/years with organic waste is 60% from the total waste. This waste will be give an impact for environment and human health (Mandal & Kaur, 2019) while solid waste give some negative impacts for human and environment, we have problem about environmental damage by industrial company. Industrial company that give some impact for environment especially in wastewater. Several studies inform that wastewater can treatments by plants (Caicedo et al., 2019), thus, we could utilize organic waste as a biomaterial that reducing wastewater.

Biochar is a new material produced by solid organic material such as coconut shell, cassava, wood, and all of organic materials. When we use biochar as a low-cost adsorbent we could save environment by solid waste caused biochar has produced by solid waste, environmental damage by wastewater and we could help socio-economy community. Recent study inform the biochar could growing up socio-economy in several community (Qambrani, Rahman, Won, Shim, & Ra, 2017)

Wastewater is dangerous material in environment, wastewater could create by mining industry (Motsi, Rowson, & Simmons, 2009), hospital (Paulus et al., 2019), food industry (Nechifor et al, 2016) and else. Wastewater has characterized by physical and chemical parametes (Wu, Yan, Zhou, & Xu, 2014) such as heavy metals content (McNamara et al., 2018), pH, temperature, salinity, BOD, COD, TSS and else (Kuyucak & St-Germain, 2016; Maya, Radin, Miau, Hashim, & Kassim, 2016; Wu et al., 2014) Wastewater have high BOD and COD content (Oladipo, Adeleye, Oladipo, & Aleshinloye, 2017) heavy metals.

Several study inform biochar could reduce heavy metals in wastewater. It caused biochar have good pores as an adsorbent, biochar could reduce heavy metals such as Cu, Ni, Cd, Zn, Al, U, Pb in many temperature for pyrolysis process. Recent study inform biochar could reducing until 95% heavy metals in wastewater with Langmuir isoterm and many mechanism (Attachment 1).

#### **CONLUSION**

In this review, a wide range of biochar properties, production techniques and applications are explained. Different pyrolysis conditions and feedstock materials influence the quantities and qualities of biochar, and can be tailored according to individual requirements. Biochar is a biomaterial by char that potential organic material for environmental management especially wastewater treatment. Biochra could reduce heavy metals such as Cu, Ni, Cd, Zn, Al, U, Pb in  $q_{max}$  are between 0.1309a until 62.7 with pyrolisis process in many temperatures and biochar sources. Isoterm adsorption of biochars are following Langmuir in many mechanisms. Experimental and modeling studies for create biochar are highly recommended for future research.

Biochar	Pyrolysis Temperature	Contaminants	Removal (%)	Qmax (mg.g <sup>-1</sup> )	Isotherm	Mechanism	Reference
Broiler litter	500	Cu	75.2	-	-	Chemisorption into a negatively charged inorganic fraction	(I. M. Lima, Boateng, & Klasson, 2010)
Broiler litter	500	Cd	21.7	-	-		
Broiler litter	500	Ni	10.1	-	-		
Broiler litter	500	Zn	16.4	-	-		
Broiler litter	700	Cu	95	-	-	Adsorption by inorganic constituent (e.g phosphorus)	(I. Lima et al., 2009)
Broiler litter	700	Cd	82.3	-	-		
Broiler litter	700	Ni	5.1	-	-		
Broiler litter	700	Zn	90.9	-	-		
Broiler litter	800	Cu	86.9	-	-	Adsorption by inorganic constituent (e.g phosphorus)	(I. Lima, Boateng, & Klasson, 2009)
Broiler litter	800	Cd	59.9	-	-		
Broiler litter	800	Ni	6	-	-		
Broiler litter	800	Zn	75.7	-	-		
Canola Straw	400	Cu(II)	-	0.59a	Langmuir	Surface complexion with carboxylic and hydrocyl functional group/adsorption through electronic attraction operating between biochar biochar surface and Cu	(Tong, Li, Yuan, & Xu, 2011)
Catle Manure	100	Al	-	0.242a	Langmuir	Surface complexion of Al to oxygen containing	(Qian L, & Chen B, 2013)
Catle Manure	400	Al	-	0.297a	Langmuir	Functional group and surface adsorption /copresipitation	(Chen et al., 2011)
Catle Manure	700	Al	-	0.243	Langmuir	Adsorption by inorganic constituent	(Chen et al., 2011)
Pine needles	600	U(VI)	-	62.7	Langmuir	PH depend adsorption	(Zhi Bin Zhang, Cao, Liang, & Liu, 2013)
pinewood	200	Pb(II)	_	3.89	Langmuir	Adsorption/diffusion into pores	(Liu & Zhang, 2009)
Rise husk	300	Pb(II)	_	1.84	Langmuir		
Rise straw	300	Pb	-	0.1309a	Langmuir	Surface complexation of Al to oxygen containing	(Qian L, & Chen B, 2013)
Rise straw	100	Al	-	0.3976a	Langmuir	Functional groups and deposition of albite	

# **Table 1.** Effect of Biochar Properties on Heavy Metals

## DAFTAR PUSTAKA

- Boddu, R., Wang, Q., Garg, A., Gopal, P., S, S., Cheng, Y.-F., & Bordoloi, S. (2018). Soil-biochar-water interactions: Role of biochar from Eichhornia crassipes in influencing crack propagation and suction in unsaturated soils. *Journal of Cleaner Production*, 210, 847–859. https://doi.org/10.1016/j.jclepro.2018.11.051
- Bridgwater, A. V. (2012). Review of fast pyrolysis of biomass and product upgrading. *Biomass and Bioenergy*, *38*, 68–94. https://doi.org/10.1016/j.biombioe.2011.01.048
- Caicedo, C., Rosenwinkel, K. H., Exner, M., Verstraete, W., Suchenwirth, R., Hartemann, P., & Nogueira, R. (2019). Legionella occurrence in municipal and industrial wastewater treatment plants and risks of reclaimed wastewater reuse: Review. Water Research, 21–34. https://doi.org/10.1016/j.watres.2018.10.080
- Chen, X., Chen, G., Chen, L., Chen, Y., Lehmann, J., McBride, M. B., & Hay, A. G. (2011). Adsorption of copper and zinc by biochars produced from pyrolysis of hardwood and corn straw in aqueous solution. *Bioresource Technology*, 102(19), 8877–8884. https://doi.org/10.1016/j.biortech.2011.06.078
- de Matos, T. N., Léon, J. J. L., Almeida, I. L. S., Marcionilio, S. M. L. O., Rezende, H. C., & Araújo, C. S. T. (2017). Elucidation of mechanism involved in adsorption of Pb(II) onto lobeira fruit (Solanum lycocarpum) using Langmuir, Freundlich and Temkin isotherms. *Microchemical Journal*, 137(Ii), 348–354. https://doi.org/10.1016/j.microc.2017.11.009
- Gupta, P., Mathur, N., Bhatnagar, P., Nagar, P., & Srivastava, S. (2009).
  Genotoxicity evaluation of hospital wastewaters. *Ecotoxicology and Environmental* Safety, 72(7), 1925–1932. https://doi.org/10.1016/j.ecoenv.2009.05.012
- Kumar, S., Loganathan, V. A., Gupta, R. B., & Barnett, M. O. (2011). An Assessment of U(VI) removal from groundwater using biochar produced from hydrothermal carbonization. *Journal of Environmental Management*, 92(10), 2504–2512. https://doi.org/10.1016/j.jenvman.2011.05.013
- Kuyucak, N., & St-Germain, P. (2016). In Situ Treatment of Acid Mine Drainage by Sulphate Reducing Bacteria in Open Pits: Scale-Up Experiences. *Journal American Society of Mining and Reclamation*, 1994(2), 303–310. https://doi.org/10.21000/jasmr94020303
- Lejano, R. P. (2019). Climate change and the relational city. *Cities*, 85(November 2018), 25–29. https://doi.org/10.1016/j.cities.2018.12.001
- Lima, I., Boateng, A., & Klasson, K. (2009). Pyrolysis of Broiler Manure: Char and Product Gas Characterization. *Industrial & Engineering Chemistry Research - IND ENG CHEM RES*, 48(3), 1292–1297. https://doi.org/10.1021/ie800989s
- Lima, I. M., Boateng, A. A., & Klasson, K. T. (2010). Physicochemical and adsorptive properties of fast-pyrolysis bio-chars and their steam activated counterparts. *Journal of Chemical Technology and Biotechnology*, 85(11), 1515–1521. https://doi.org/10.1002/jctb.2461

- Liu, Z., & Zhang, F. S. (2009). Removal of lead from water using biochars prepared from hydrothermal liquefaction of biomass. *Journal of Hazardous Materials*, 167(1–3), 933–939. https://doi.org/10.1016/j.jhazmat.2009.01.085
- Mandal, R., & Kaur, S. (2019). Impact of environmental pollution on trace elements in vegetables and associated potential risk to human health in industrial town Mandi-gobindgarh (India). *Chemosphere*, 219, 574–587. https://doi.org/10.1016/j.chemosphere.2018.12.034
- Maya, R., Radin, S., Miau, J. A., Hashim, A., & Kassim, M. (2016). Multicomponent Filters for Domestic Graywater Treatment in Village Houses, (July), 405–415. https://doi.org/10.5942/jawwa.2016.108.0103
- McNamara, P., Hughes, M., Anderson, E., Liu, Z., Zitomer, D., Singer, S, Kimbell, L. (2018). Characteristics and applications of biochars derived from wastewater solids. *Renewable and Sustainable Energy Reviews*, 90(November 2017), 650–664. https://doi.org/10.1016/j.rser.2018.02.040
- Motsi, T., Rowson, N. A., & Simmons, M. J. H. (2009). Adsorption of heavy metals from acid mine drainage by natural zeolite. *International Journal of Mineral Processing*, 92(1–2), 42–48. https://doi.org/ 10.1016/j.minpro.2009.02.005
- Nechifor, A.-C., Passeri, P., Dima, S.-O., Ghimpusan, M., & Nechifor, G. (2016). Case studies on the physical-chemical parameters' variation during three different purification approaches destined to treat wastewaters from food industry. *Journal of Environmental Management*, 203, 811–816. https://doi.org/10.1016/j.jenvman.2016.07.030
- Nzediegwu, C., Prasher, S., Elsayed, E., Dhiman, J., Mawof, A., & Patel, R. (2019). Effect of biochar on heavy metal accumulation in potatoes from wastewater irrigation. *Journal of Environmental Management*, 232(October 2018), 153–164. https://doi.org/10.1016/j.jenvman.2018.11.013
- Oladipo, A. A., Adeleye, O. J., Oladipo, A. S., & Aleshinloye, A. O. (2017). Bioderived MgO nanopowders for BOD and COD reduction from tannery wastewater. *Journal of Water Process Engineering*, 16, 142–148. https://doi.org/10.1016/j.jwpe.2017.01.003
- Paulus, G. K., Hornstra, L. M., Alygizakis, N., Slobodnik, J., Thomaidis, N., & Medema, G. (2019). The impact of on-site hospital wastewater treatment on the downstream communal wastewater system in terms of antibiotics and antibiotic resistance genes. *International Journal of Hygiene and Environmental Health*, (October 2018), 0–1. https://doi.org/10.1016/j.ijheh.2019.01.004
- Pfennigstorf, W. (1979). *Compensation THE MARGINS : Environment , Damages , and Compensation*. American Bar Foundation.
- Qambrani, N. A., Rahman, M. M., Won, S., Shim, S., & Ra, C. (2017). Biochar properties and eco-friendly applications for climate change mitigation, waste management, and wastewater treatment: A review. *Renewable and Sustainable Energy Reviews*, 79(November 2016), 255–273. https://doi.org/10.1016/j.rser.2017.05.057
- Ruokonen, E., & Temmes, A. (2019). The approaches of strategic environmental management used by mining companies in Finland. *Journal of Cleaner Production*, *210*, 466–476. https://doi.org/10.1016/j.jclepro.2018.10.273

- Sun, D., Zhang, D.-X., Wu, W., Wu, P., Zhou, Y.-K., & Yang, F. (2018). Assessment of heavy metal pollution and human health risks in urban soils around an electronics manufacturing facility. *Science of The Total Environment*, 630, 53–61. https://doi.org/10.1016/j.scitotenv.2018.02.183
- Tong, X. J., Li, J. Y., Yuan, J. H., & Xu, R. K. (2011). Adsorption of Cu(II) by biochars generated from three crop straws. *Chemical Engineering Journal*, 172(2–3), 828–834. https://doi.org/10.1016/j.cej.2011.06.069
- Wu, J., Yan, G., Zhou, G., & Xu, T. (2014). Wastewater COD biodegradability fractionated by simple physical-chemical analysis. *Chemical Engineering Journal*, 258, 450–459. https://doi.org/10.1016/j.cej.2014.07.106
- Xu, H., Li, L., Wang, C., Xie, Y., Liu, H., Zhang, A., and Xu, F. (2018). Effect of modified coconut shell biochar on availability of heavy metals and biochemical characteristics of soil in multiple heavy metals contaminated soil. *Science of The Total Environment*, 645, 702–709. https://doi.org/10.1016/j.scitotenv.2018.07.115
- Zhang, Z. Bin, Cao, X. H., Liang, P., & Liu, Y. H. (2013). Adsorption of uranium from aqueous solution using biochar produced by hydrothermal carbonization. *Journal of Radioanalytical and Nuclear Chemistry*, 295(2), 1201–1208. https://doi.org/10.1007/s10967-012-2017-2
- Zhang, Z., Zhu, Z., Shen, B., & Liu, L. (2019). Insights into biochar and hydrochar production and applications: A review. *Energy*, *171*, 581–598. https://doi.org/10.1016/j.energy.2019.01.03.